




# COOLSOURCE

## FLUROPON® SR COLOR PALETTE



**Regal White**  
SR .68 E .86



**Brook Blue**  
SR .29 E .85



**Aged Copper**  
SR .47 E .85



**Terra Cotta**  
SR .35 E .87



**Copper**  
SR .49 E .85



**Stone White**  
SR .60 E .86



**Pacific Blue**  
SR .26 E .85




**Patina Green**  
SR .29 E .87



**Colonial Red**  
SR .33 E .85



**Napa Champagne**  
SR .37 E .80



**Solar White**  
SR .68 E .85



**Cobalt Stone**  
SR .26 E .85



**Hemlock Green**  
SR .32 E .86



**Burgundy**  
SR .25 E .85



**Nevada Silver**  
SR .60 E .77



**Sandstone**  
SR .54 E .86



**Medium Bronze**  
SR .30 E .87



**Wood Duck Teal**  
SR .25 E .86



**Regal Red**  
SR .42 E .84



**Weather Galvalume**  
SR .30 E .79



**Sierra Tan**  
SR .35 E .86




**Mansard Brown**  
SR .27 E .86



**Evergreen**  
SR .27 E .86



**Ash Gray**  
SR .39 E .84




**Slate Gray**  
SR .36 E .84




**Galvalume**  
SR .69 E .06



**Dark Bronze**  
SR .26 E .84



**Hartford Green**  
SR .30 E .85



**Charcoal Gray**  
SR .29 E .84



**Matte Black**  
SR .27 E .86

Colors shown closely approximate actual coating colors.  
Actual color samples on metal substrates are available upon request.



SR: Solar Reflectance  
E: Emittance